


PA 12C OFN

PA 12C + Oil

Building on the exceptional properties of PA 12C comes the further enhanced PA 12C + OFN. A complex blended oil lubrication system uniformly distributed throughout the product guarantees consistent performance over the whole service life of this versatile oil-loaded nylon.

PROPERTY	TEST METHOD	NOTES	METRIC UNITS		IMPERIAL UNITS	
GENERAL						
Colour			Yellow / Black		Yellow / Black	
Density	ISO 1183:1987	Test Method A	g/cm ³	1.030	lb/inch ³	-
Moisture Absorption (Equilibrium)	ISO 62:1999	50% RH, 23C	%	0.9	%	0.7
Water Absorption (24 Hours)	ISO 62:1999 (modified)	Immersion, 23C	%	-	%	-
Water Absorption (Saturation)	ISO 62:1999	Immersion, 23C	%	1.40	%	1.60
MECHANICAL						
Tensile strength	ISO 527-1/2:1993	Sample Type 1B, 50mm min ⁻¹	MPa	60	psi	8706
E-modulus	ISO 527-1/2:1993	Sample Type 1B, 50mm min ⁻¹	MPa	2000	psi	290200
Elongation at break	ISO 527-1/2:1993	Sample Type 1B, 50mm min ⁻¹	%	>8	%	>8
Compressive Strength	ISO 604:2002	Sample Type B, 5mm min ⁻¹	MPa	70	psi	10150
Compressive Modulus	ISO 604:2002	Sample Type A, 1mm min ⁻¹	MPa	1500	psi	217650
Flexural Strength*	ISO 178:2001	1.5mm min ⁻¹	MPa	62	psi	8996
Flexural Modulus	ISO 178:2001	1.5mm min ⁻¹	MPa	1650	psi	239415
Izod Impact Strength	ISO 180:2000	Sample Type A (Notched)	KJ/m ²	>10	ft.lb/in ²	4.76
Charpy Impact Strength	ISO 179-2:1999	Notched	KJ/m ²	-	ft.lb/in ²	-
Hardness (Shore D)	ISO 868:2003	-	-	75	-	75
Coefficient of Friction (Dynamic)	-	31.4m/min, 1.75MPa	-	0.38	-	0.38
Limiting PV	-	-	MPa/m.min	-	psi.ft/min	-
Wear Rate	-	31.4m/min, 1.75MPa	mg/km	-	-	-
K-Factor	-	31.4m/min, 1.75MPa	mm ³ /Nm	-	in ³ .min./ft.lb.hr	-
THERMAL						
Melting Temperature	-	-	°C	178	°F	351
Glass Transition Temperature (Tg)	ISO 11359-2:1999	-	°C	-	°F	-
Heat Deflection Temperature HDT/A	ISO 75	1.80MPa	°C	-	°F	-
Heat Deflection Temperature HDT/B	ISO 75	0.45MPa	°C	-	°F	-
Maximum Intermittent Service Temperature	-	-	°C	150	°F	302
Maximum Continuous Service Temperature	-	5000hrs	°C	110	°F	230
Minimum Intermittent Service Temperature	-	-	°C	-	°F	-
Minimum Continuous Service Temperature	-	-	°C	-40	°F	-40
Coefficient of Linear Thermal Expansion (TMA)	ISO 11359-2:1999	23°C - 55°C	°C ⁻¹	10 x 10 ⁻⁵	°F ⁻¹	-
Thermal Conductivity	ISO 8301:1991	Mean T = 20°C	W/m.°C	0.25	BTU in/ft.hr.°F	-
Flammability	IEC 60695-11-10:2003-08	-	-	HB	-	HB
ELECTRICAL						
Dielectric Constant	IEC 60250:1969-01	1MHz	-	3.5	-	3.5
Dielectric Constant (Low Frequency)	-	100Hz	-	-	-	-
Dissipation Factor	IEC 60250:1969-01	100 Hz	Hz	-	Hz	-
Dielectric Strength	IEC 60243-1:1998-01	-	kV/mm	35	kV/in	-
Volume Resistivity	IEC 60093:1980-01	-	ohm.m	1 x 10 ¹²	ohm.in	1 x 10 ¹²
Surface Resistivity ROA	IEC 60093:1980-01	-	ohm	1 x 10 ¹²	ohm	1 x 10 ¹²
Comparative Tracking Index	IEC 60112:2003-01	-	CTI	-	CTI	-
AVAILABILITY						
ROD: 20mm - 190mm DIA		All information contained in this literature corresponds with our current knowledge of the products. Global EPP assume no liability whatsoever in respect of application, conversion or use made of the aforementioned information or products, or any consequence thereof. The buyer undertakes all liability in respect of the application, conversion or use of the aforementioned information or products. Existing intellectual property rights must be observed and Global EPP reserve the right to make technical alterations.				
PLATE: 6mm - 100mm THICK	