


PA 6E

This general purpose grade offers an excellent blend of mechanical and impact strength, vibration damping and wear resistance. Complimenting these properties are good electrical insulation and favourable chemical resistance.

PROPERTY	TEST METHOD	NOTES	METRIC UNITS		IMPERIAL UNITS	
GENERAL						
Colour				Natural / Black		Natural / Black
Density	ISO 1183:1987	Test Method A	g/cm ³	1.135	lb/inch ³	0.041
Moisture Absorption (Equilibrium)	ISO 62:1999	50% RH, 23C	%	3	%	3
Water Absorption (24 Hours)	ISO 62:1999 (modified)	Immersion, 23C	%	-	%	-
Water Absorption (Saturation)	ISO 62:1999	Immersion, 23C	%	9.50	%	9.50
MECHANICAL						
Tensile strength	ISO 527-1/2:1993	Sample Type 1B, 50mm min ⁻¹	MPa	80	psi	10878
E-modulus	ISO 527-1/2:1993	Sample Type 1B, 50mm min ⁻¹	MPa	3500	psi	507633
Elongation at break	ISO 527-1/2:1993	Sample Type 1B, 50mm min ⁻¹	%	>30	%	>30
Compressive Strength	ISO 604:2002	Sample Type B, 5mm min ⁻¹	MPa	90	psi	13053
Compressive Modulus	ISO 604:2002	Sample Type A, 1mm min ⁻¹	MPa	2600	psi	377099
Flexural Strength*	ISO 178:2001	1.5mm min ⁻¹	MPa	80	psi	11603
Flexural Modulus	ISO 178:2001	1.5mm min ⁻¹	MPa	2100	psi	304580
Izod Impact Strength	ISO 180:2000	Sample Type A (Notched)	KJ/m ²	8.00	ft.lb./in ²	3.81
Charpy Impact Strength	ISO 179-2:1999	Notched	KJ/m ²	-	ft.lb./in ²	-
Hardness (Shore D)	ISO 868:2003		-	82	-	82
Coefficient of Friction (Dynamic)		31.4m/min, 1.75MPa	-	-	-	-
Limiting PV			MPa/m.min	-	psi.ft/min	-
Wear Rate		31.4m/min, 1.75MPa	mg/km	-	-	-
K-Factor		31.4m/min, 1.75MPa	mm ³ /Nm	-	in ³ .min./ft.lb.hr	-
THERMAL						
Melting Temperature	-		°C	220	°F	428
Glass Transition Temperature (Tg)	ISO 11359-2:1999		°C	60	°F	140
Heat Deflection Temperature HDT/A	ISO 75	1.80MPa	°C	70	°F	158
Heat Deflection Temperature HDT/B	ISO 75	0.45MPa	°C	160	°F	320
Maximum Intermittent Service Temperature	-		°C	160	°F	320
Maximum Continuous Service Temperature	-	5000hrs	°C	90	°F	158
Minimum Intermittent Service Temperature	-		°C	-	°F	-
Minimum Continuous Service Temperature	-		°C	-40	°F	-40
Coefficient of Linear Thermal Expansion (TMA)	ISO 11359-2:1999	23°C - 55°C	°C ⁻¹	8.5 x 10 ⁻⁵	°F ⁻¹	4.72 x 10 ⁻⁵
Thermal Conductivity	ISO 8301:1991	Mean T = 20°C	W/m.°C	0.28	BTU in/ft.hr.°F	0.16
Flammability	IEC 60695-11-10:2003-08		-	HB	-	HB
ELECTRICAL						
Dielectric Constant	IEC 60250:1969-01	1MHz	-	3.5	-	3.5
Dielectric Constant (Low Frequency)		100Hz	-	3.9	-	3.9
Dissipation Factor	IEC 60250:1969-01	100 Hz Hz 0.021 Hz 0.021				
Dielectric Strength	IEC 60243-1:1998-01		kV/mm	25	kV/in	635
Volume Resistivity	IEC 60093:1980-01		ohm.m	1 x 10 ¹³	ohm.in	3.93 x 10 ¹⁴
Surface Resistivity ROA	IEC 60093:1980-01		ohm	1 x 10 ¹²	ohm	1 x 10 ¹²
Comparative Tracking Index						
AVAILABILITY						
ROD: 5mm - 150mm DIA		All information contained in this literature corresponds with our current knowledge of the products. Global EPP assume no liability whatsoever in respect of application, conversion or use made of the aforementioned information or products, or any consequence thereof. The buyer undertakes all liability in respect of the application, conversion or use of the aforementioned information or products. Existing intellectual property rights must be observed and Global EPP reserve the right to make technical alterations.				
PLATE: 6mm - 60mm THICK	