




# WFN

## PA 6C + Wax

WFN uses a single wax lubricant uniformly distributed to improve wear resistance and coefficient of friction characteristics. The material has excellent mechanical, thermal and electrical properties and exhibits excellent Pressure-Velocity capabilities.

PROPERTY	TEST METHOD	NOTES	METRIC UNITS	IMPERIAL UNITS		
<b>GENERAL</b>						
Colour			Grey	Grey		
Density	ISO 1183:1987	Test Method A	g/cm <sup>3</sup>	1.145 lb/inch <sup>3</sup>	0.041	
Moisture Absorption (Equilibrium)	ISO 62:1999	50% RH, 23C	%	-	-	
Water Absorption (24 Hours)	ISO 62:1999 (modified)	Immersion, 23C	%	0.3	0.3	
Water Absorption (Saturation)	ISO 62:1999	Immersion, 23C	%	5.3	5.3	
<b>MECHANICAL</b>						
Tensile strength	ISO 527-1/2:1993	Sample Type 1B, 50mm min <sup>-1</sup>	MPa	80	psi	11603
E-modulus	ISO 527-1/2:1993	Sample Type 1B, 50mm min <sup>-1</sup>	MPa	4000	psi	580152
Elongation at break	ISO 527-1/2:1993	Sample Type 1B, 50mm min <sup>-1</sup>	%	>20	%	>20
Compressive Strength	ISO 604:2002	Sample Type B, 5mm min <sup>-1</sup>	MPa	95	psi	13779
Compressive Modulus	ISO 604:2002	Sample Type A, 1mm min <sup>-1</sup>	MPa	2600	psi	377099
Flexural Strength*	ISO 178:2001	1.5mm min <sup>-1</sup>	MPa	105	psi	15229
Flexural Modulus	ISO 178:2001	1.5mm min <sup>-1</sup>	MPa	3200	psi	464122
Izod Impact Strength	ISO 180:2000	Sample Type A (Notched)	KJ/m <sup>2</sup>	6.00	ft.lb./in <sup>2</sup>	2.86
Charpy Impact Strength	ISO 179-2:1999	Notched	KJ/m <sup>2</sup>	-	ft.lb./in <sup>2</sup>	-
Hardness (Shore D)	ISO 868:2003		-	84	-	84
Coefficient of Friction (Dynamic)		31.4m/min, 1.75MPa	-	0.10	-	0.10
Limiting PV			MPa/m.min	-	psi.ft/min	-
Wear Rate		31.4m/min, 1.75MPa	mg/km	0.06	-	-
K-Factor		31.4m/min, 1.75MPa	mm <sup>3</sup> /Nm	0.70 x 10 <sup>-6</sup>	in <sup>3</sup> .min./ft.lb.hr	0.34 x 10 <sup>-9</sup>
<b>THERMAL</b>						
Melting Temperature	-		°C	220	°F	428
Glass Transition Temperature (Tg)	ISO 11359-2:1999		°C	-	°F	-
Heat Deflection Temperature HDT/A	ISO 75	1.80MPa	°C	-	°F	-
Heat Deflection Temperature HDT/B	ISO 75	0.45MPa	°C	-	°F	-
Maximum Intermittent Service Temperature	-		°C	180	°F	356
Maximum Continuous Service Temperature	-	5000hrs	°C	110	°F	230
Minimum Intermittent Service Temperature	-		°C	-100	°F	-148
Minimum Continuous Service Temperature	-		°C	-40	°F	-40
Coefficient of Linear Thermal Expansion (TMA)	ISO 11359-2:1999	23°C - 55°C	°C <sup>-1</sup>	8 x 10 <sup>-5</sup>	°F <sup>-1</sup>	4.44 x 10 <sup>-5</sup>
Thermal Conductivity	ISO 8301:1991	Mean T = 20°C	W/m.°C	-	BTU in/ft.hr.°F	-
Flammability	IEC 60695-11-10:2003-08		-	HB	-	HB
<b>ELECTRICAL</b>						
Dielectric Constant	IEC 60250:1969-01	1MHz	-	3.7	-	3.7
Dielectric Constant (Low Frequency)		100Hz	-	4	-	4
Dissipation Factor	IEC 60250:1969-01	100 Hz	Hz	-	Hz	-
Dielectric Strength	IEC 60243-1:1998-01		kV/mm	25	kV/in	635
Volume Resistivity	IEC 60093:1980-01		ohm.m	1 x 10 <sup>13</sup>	ohm.in	3.93 x 10 <sup>14</sup>
Surface Resistivity ROA	IEC 60093:1980-01		ohm	1 x 10 <sup>12</sup>	ohm	1 x 10 <sup>12</sup>
Comparative Tracking Index	IEC 60112:2003-01		CTI	600	CTI	600
<b>AVAILABILITY</b>						
ROD: 10mm - 500mm DIA		All information contained in this literature corresponds with our current knowledge of the products. Global EPP assume no liability whatsoever in respect of application, conversion or use made of the aforementioned information or products, or any consequence thereof. The buyer undertakes all liability in respect of the application, conversion or use of the aforementioned information or products. Existing intellectual property rights must be observed and Global EPP reserve the right to make technical alterations.				
PLATE: 6mm - 120mm THICK						
TUBE: 45mm - 1500mm						



# Global EPP

UK Conqueror House, Hastings Road  
Leicester LE5 0HU  
Tel. +44 (0)116 246 3311  
Email. sales-uk@globalepp.com

USA 2301 Duss Ave, Suite 27  
Ambridge, PA 15003  
Tel. +1 412 580 4780  
Email. sales-usa@globalepp.com

www.globalepp.com